

MECHANICAL EQUIPMENT

# Products

## Friction Linings

ZA GOLD

# Ferotec Friction Ltd

## ZAGOLD Product Data Sheet

### General Description

**ZAGOLD** is a solid woven friction material. It is based on yarn spun from a blend of glass and synthetic fibres together with a fine brass wire to enhance its strength and heat dissipation properties. The impregnant has been specially developed to give it good frictional properties combined with a fair degree of flexibility. It has a high coefficient of friction with excellent fade resistance and is particularly suitable for mine winder brakes. To help during fitting to brake shoes and bands it can be softened and made more pliable by warming in a bonding oven to between 150 & 180°C for sufficient time for the heat to penetrate the fabric. This material is not suited to operate in oil-immersed conditions.

### Applications

Industrial drum and band brake linings  
 Mine winder brake linings

### Bonding

**ZAGOLD** may be bonded using any of the established adhesives recommended for friction material. However, to obtain the best results it is necessary to use a thermosetting adhesive.

### Mating Surface

A good quality, fine grained, pearlitic cast iron or cold rolled steel with a Brinell hardness of 180. Cast steels are not recommended.

### Availability

- **Roll**  
 Length 10.0 Metres  
 Width 20 to 510mm  
 Thickness range 12.7mm to 25.4mm
- Sheet size 1000mm x 660mm x 12.7mm to 25.4mm thick
- Linings and special shapes available on request

### TECHNICAL DATA

#### Friction

$\mu$  for design purposes :  
 Static (cold) 0.45  
 Dynamic (dry) 0.43

#### Recommended Operating Range

Pressure	Dynamic	0.1—1.00 MPa
	Static	0.1 - 2.50 MPa
Max. rubbing speed	25 m/s	
Max. continuous temperature	150°C	
Max. intermittent temperature	200°C	
Max. temperature	300°C	

#### Test Conditions

Application Speed	15m/s
Clamping pressure	0.61 MN/m <sup>2</sup> (88.5 lbf/in <sup>2</sup> )
Average temperature	Initial Bedding 140°C
Average temperature	Pressure Sensitivity / Speed Sensitivity 80°C

### PHYSICAL PROPERTIES

Density	1.45-1.65 g/cc
Ultimate tensile strength	60 MPa
Ultimate compressive strength	100 MPa
Resistance to compression (Test thickness 9.5mm)	2.5% 5.17 MPa 5.0% 13.62 MPa 7.5% 22.75 MPa
Ultimate shear strength	16 MPa
Rivet holding capacity	135 MPa

(All physical properties shown above are all mean values)

The information supplied in this data sheet is believed to be accurate and reliable, and was obtained by scientific and laboratory testing. However, since actual conditions of use are largely outside the control of FEROTEC FRICTION LIMITED, it is suggested that this material be thoroughly tested under actual conditions of use before final acceptance.

Issue 4 Jun 10

Represented by  
**ACTOM Mechanical Equipment**  
 Tel : 011 8783000 Fax : 011 8783001

Ferotec Friction Ltd

Unit C Greenfield Business Park, Bagillt Rd, Holywell, Flintshire CH8 7HJ, United Kingdom

Tel: +44 1352 710360 Fax: +44 1352 719368 E-mail: ffsales@ferotecfriction.co.uk Website: www.ferotecfriction.com

